

PRODUCT DESCRIPTION

TWO COMPONENT EPOXY PRIMER RED IRON OXIDE 74750

(CURING AGENT 20080)

RSI PRIMER 74750 is designed for use as a high performance inhibitive primer base on epoxy and polyamide resins and red iron oxide as inhibitive pigments with an excellent anticorrosive efficiency in moderate to severe environment.

RSI PRIMER 74750 can be applied as an inhibitive primer on blasted steel structure.

Standard color availability Manufactured only in light gray and off white color.

GENERAL PROPERTIES

Adhesion	Excellent to both grit blasted and manually prepared surfaces.	
Corrosion Resistance	Excellent on correctly prepared surfaces.	
Temperature resistance	Dry: Maximum 130 °C	Wet: Maximum 50 °C

PHYSICAL PROPERTIES:

Colors/Shade No	Red
Finish	Flat
Volume Solid	60%
Theoretical spreading rate	12 m ² /liter 50 Mic. Dft.
Flash point	30 °C
Specific gravity	1.45-1.55 kg/liter
V.O.C.	Max. 280 gr/liter
Shelf life	1 Years (25°C / 77°F) from time of production. Depending on storage condition, mechanical stirring may be necessary before usage.

MIXING

Mixing ratio (by weight)	Component A 74750 8	Component B 20080 1
Pot life	8 hours (20 °C/ 68 °F)	

APPLICATION

Conditions	Do not apply when relative humidity exceeds 80% or when the surface to be coated is less than 3 °C above the dew point.	
Method	Airless sprays	Brush (touch-up)
Thinner (max. vol.)	1051 (10-30%)	1051 (5%)
Spray setting		
Pump ratio minimum	30:1	
Tip size	0.019” - 0.021”	
Tip pressure	150 bar / 2200 Psi (Airless spray data are indicative and subject to adjustment)	
Cleaning of tools	Thinner 1051	
Indicated film thickness, dry	60 microns	
Indicated film thickness, wet	100 microns	

DRYING AND CURING TIMES AT (20 °C)

Dry to touch	Max.1 hour
Hard dry	24 hours
Full curing	7 days
Recoat interval, min	8 hours
Recoat interval, max	7 days , see REMARKS

SURFACE PREPARATION

New steel Steel surface should ideally be abrasive blast cleaning to minimum Sa 2½. The surface must be completely clean and dry prior to application. And its temperature must be above the dew point to avoid condensation.

REMARKS

PRECEDING COAT: None.

SUBSEQUENT COAT: EPOXY INTER MEDIATE and Epoxy Top coat.

Film thickness: May be specified in another film thickness than indicated depending on purpose and area of use.

This will alter spreading rate and may influence drying time and recoating intervals. Normal range is 50-75 microns/ 2-3 mils.

Thinning: The type and amount of thinner depend on application conditions, application method, temperature, ventilation, and substrate. Thinner 1051 is recommended in general.

Recoating And drying/curing Time

Physical data versus temperatures:					
Surface temperature		5°C/41°F	10°C/50°F	20°C/68°F	30°C/86°F
Dry to touch approx.		12 hours	8 hours	4 hours	3 hours
Resist condensing humidity/ light showers after		4 days	2 days	24 hours	12 hours
Fully cured		20 days	14 days	7 days	5 days
Recoating interval with epoxy intermediate	Min	24 hours	16 hours	8 hours	4 hours
	Max	15 days	12 days	7 days	5 days

A completely clean surface is mandatory to ensure intercoat adhesion, especially at long recoating intervals. Any dirt, oil, and grease have to be removed, e.g. with suitable detergent. Salts to be removed by fresh water hosing. To check an adequate quality of the surface cleaning a test patch is recommended before actual recoating.

SAFETY

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult RSI material safety data sheets and follow all local and national safety regulations. Harmful or fatal if swallowed; immediately seek medical assistance. Avoid inhalations of possible solvent vapors or paint mist, as well as paint contact with skin and eyes. Apply only on well-ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant. Always take precautions against the risks of fire and explosions.

Mar 2010

Ranghay e Sanati e Iran Co.
Product data sheet 74750

RSI
COATING