

## PRODUCT DESCRIPTION

### ZINC SILICATE PRIMER 74360

RSI ZINCSILICATE 74360 is a two-component, solvent-borne, self-curing, inorganic zinc silicate with outstanding resistance against weathering and abrasion. It has excellent chemical resistance within the pH range 6-9. For service temperature range, see below. Applicable by airless spray. Offers cathodic protection of local mechanical damage.

RSI ZINCSILICATE 74360 is designed for a general purpose, heavy-duty, rust-preventing primer. And As a single, complete coating for long-term protection of steel exposed moderately to severely corrosive environment and to abrasion.

Standard color availability Metal gray.

## GENERAL PROPERTIES

<b>Adhesion</b>	Min. 4B on SA2 ½ blasted and cleans surfaces.
<b>Temperature resistance</b>	<ul style="list-style-type: none"><li>• Resistant to permanent dry temperatures up to 500°C/932°F.</li><li>• Resistant to occasional short-term heating (peak temperatures) up to 500°C/932°F while permanent service temperatures are otherwise below 400°C/752°F.</li><li>• In the case of cyclic service conditions with regular periods of low and high temperatures, the temperature should be kept below 400°C/752°F. In the case of service temperatures above 400°C/752°F, it is of advantage to apply a topcoat of RSI SILICONE ALUMINIUM 53465</li></ul>

## PHYSICAL PROPERTIES:

<b>Colors/Shade No</b>	Metal grey/7023
<b>Finish</b>	Flat
<b>Volume Solid</b>	64 %
<b>Theoretical spreading rate</b>	12.8 m <sup>2</sup> /liter 50 Mic. Dft.
<b>Flash point</b>	15 °C
<b>Specific gravity</b>	2.65 kg/liter
<b>V.O.C.</b>	Max. 140 gr/liter
<b>Shelf life</b>	3 Mount (25°C/77°F) from time of production. Shelf life is dependent on storage temperature. Shelf life is reduced at storage temperatures above 25°C/77°F. Do not store above 40°C/104°F. Shelf life is exceeded if the liquid is gelled or if the mixed product forms gels before application.

## MIXING

<b>Mixing ratio (by weight)</b>	Component A 74360 32	Component B 24360 68
<b>Pot life</b>	8 hours (20 °C/ 68 °F)	

## APPLICATION

<b>Conditions</b>	The surface must be completely clean and dry with a temperature above the dew point to avoid condensation. At temperatures ranging from -10°C/15°F to 40°C/105°F. Curing needs minimum 65% relative humidity.		
<b>Method</b>	Airless spray	Air spray	Brush (touch-up)
<b>Thinner (max. vol.)</b>	3060 (30%)	3060(50%)	3060 (10%)
<b>Spray setting</b>			
<b>Pump ratio minimum</b>	30:1		
<b>Tip size</b>	0.019” – 0.023”	1.8 mm	
<b>Tip pressure</b>	100 bar / 1500 Psi	5 – 6 bar	
	(Airless spray data are indicative and subject to adjustment)		
<b>Cleaning of tools</b>	Thinner 3060		
<b>Indicated film thickness, dry</b>	50 microns		
<b>Indicated film thickness, wet</b>	75 microns		

## DRYING AND CURING TIMES AT 20°C/68°F (65-75% RH)

<b>Dry to touch</b>	30 (approx.) min.
<b>Full curing</b>	3 (approx.) days
<b>Recoat interval, min</b>	8 hours
<b>Recoat interval, max</b>	None, see REMARKS

---

## SURFACE PREPARATION

<b>Surface condition</b>	Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high-pressure) fresh water cleaning. Grit blasting to minimum Sa 2½ with a surface profile equivalent to Rugotest No. 3, BN10a, and Keane-Tator Comparator, min. 3.0 G /S, or ISO Comparator rough MEDIUM (G). In case of new steel to be exposed to no more than medium aggressive (industrial) environment and without any extraordinary demands to lifetime, a surface preparation degree of SSPC-SP6 may suffice.
<b>Maintenance</b>	Touch-up with zinc rich epoxy primer quality is recommended prior to application of mid coats.

---

## REMARKS

<b>SUBSEQUENT COAT:</b>	None or according to specification.
<b>RECOATING:</b>	Minimum interval at 20°C/68°F, 65-75% RH for recoating with: RSI HB 63150 (system/high-build) 3 days, RSI HB 63150 (25 micron/1 mil) 24 hours. Recoating intervals are strongly dependent on both temperature and humidity. Deviations from the standard conditions may shorten or prolong the recoating intervals. The recoating interval of 24 hours for 25 micron/1 mil RSI HB 63150 is only valid in case the subsequent coat is applied more than 1 week after (20°C/68°F), 75% RH, and humid weather. Otherwise, the minimum recoating interval is the same as for system/high-build.
<b>Film thickness:</b>	If top coated with a heavy- duty system, 50 micron/2 mils dry film thickness (75 micron/3 mils wet) is recommended. For long-term protection without topcoat, 75 micron/3 mils dry film thickness (100-125 micron/4-5mils wet) is generally recommended. In tanks 100 micron/4 mils dry film thickness (150 micron/6 mils wet) is recommended but may be applied in 125 micron/5 mils dry film thickness (200 micron/8 mils wet).
<b>Thinning:</b>	The type and amount of thinner depend on application conditions, application method, temperature, ventilation, and substrate. Thinner 3060 is recommended in general.

**A completely clean surface is mandatory to ensure intercoat adhesion, especially at long recoating intervals. Any dirt, oil, and grease have to be removed, e.g. with suitable detergent. Salts to be removed by fresh water hosing. To check an adequate quality of the surface cleaning a test patch is recommended before actual recoating.**

---

## SAFETY

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult RSI material safety data sheets and follow all local and national safety regulations. Harmful or fatal if swallowed; immediately seek medical assistance. Avoid inhalations of possible solvent vapors or paint mist, as well as paint contact with skin and eyes. Apply only on well-ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant. Always take precautions against the risks of fire and explosions.

Mar 2010

Ranghay e Sanati e Iran Co.  
Product data sheet 74360

**RSI**  
**COATING**