

PRODUCT DESCRIPTION

ONE COMPONENT AIR DRY PRIMER ZP 74645

RSI PRIMER ZP 74645 is designed for use as an anti corrosive and inhibitive quick-drying primer base on urethane alkyd resin and Zinc phosphate as inhibitive pigment with a good anticorrosive efficiency in mild to moderate environment. RSI PRIMER ZP 74645 can be applied as an inhibitive primer on blasted steel structure.

Standard color availability Manufactured only in light gray and off white color.

GENERAL PROPERTIES

Adhesion	Good to both grit blasted and manually prepared surfaces.
Corrosion Resistance	Good on correctly prepared surfaces.
Temperature resistance	Dry: Maximum 90 °C

PHYSICAL PROPERTIES:

Colors/Shade No	Grey/7011/RAI NO
Finish	Semi Flat
Volume Solid	45%
Theoretical spreading rate	9 m ² /liter 50 Mic. Dft.
Flash point	38 °C
Specific gravity	1.3 kg/liter
V.O.C.	Max. 450 gr/liter
Shelf life	1 Year (25°C / 77°F) from time of production. Depending on storage condition, mechanical stirring may be necessary before usage.

APPLICATION

Conditions	Do not apply when relative humidity exceeds 80% or when the surface to be coated is less than 3 °C above the dew point.		
Method	Airless sprays	Air spray	Brush (touch-up)
Thinner (max. vol.)	30040 (10%)	30040(25%)	30040 (5%)
Spray setting			
Pump ratio minimum	30:1		
Tip size	.021”	1.8 mm	
Tip pressure	150 bar / 2200 Psi	4 – 5 bar	
	(Airless spray data are indicative and subject to adjustment)		
Cleaning of tools	Thinner 30040		
Indicated film thickness, dry	75 microns		
Indicated film thickness, wet	175 microns		

Issued:

April 2009

DRYING AND CURING TIMES AT (20 °C)

Dry to touch	4 hour
Hard dry	48 hours
Full curing	15 days
Recoat interval, min	8 hours
Recoat interval, max	15 days , see REMARKS

SURFACE PREPARATION

New steel	Steel surface should ideally be abrasive blast cleaning to minimum Sa 2. The surface must be completely clean and dry prior to application. And its temperature must be above the dew point to avoid condensation.
Maintenance	Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high pressure) fresh water cleaning. Remove all rust and loose material by abrasive blasting or power tool cleaning. Dust off residues. Touch up to full film thickness.

REMARKS

PRECEDING COAT:	None.
SUBSEQUENT COAT:	AIR DRYING ALKYD INTER MEDIATE OR TOP COAT.
Film thickness:	May be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate and may influence drying time and recoating intervals. Normal range is 75 microns/ 3 mils.
Thinning:	The type and amount of thinner depend on application conditions, application method, temperature, ventilation, and substrate. Thinner 30040 is recommended in general.
Recoating And drying/curing Time	

Physical data versus temperatures in mild atmosphere:					
Surface temperature	5°C/41°F	10°C/50°F	20°C/68°F	30°C/86°F	
Dry to touch approx.	12 hours	6 hours	4 hours	2 hours	
Resist condensing humidity/ light showers after	4 days	2 days	48 hours	24 hours	
Fully cured	20 days	14 days	15 days	10 days	
Recoating interval with alkyd intermediate	Min	48 hours	16 hours	8 hours	4 hours
	Max	None	None	None	None

Maximum recoating interval in moderate atmosphere is 15 days.

A completely clean surface is mandatory to ensure intercoat adhesion, especially at long recoating intervals. Any dirt, oil, and grease have to be removed, e.g. with suitable detergent. Salts to be removed by fresh water hosing. To check an adequate quality of the surface cleaning a test patch is recommended before actual recoating.

SAFETY

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult RSI material safety data sheets and follow all local and national safety regulations. Harmful or fatal if swallowed; immediately seek medical assistance. Avoid inhalations of possible solvent vapors or paint mist, as well as paint contact with skin and eyes. Apply only on well-ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant. Always take precautions against the risks of fire and explosions.

April 2009

Ranghay e Sanati e Iran Co.
Product data sheet ZP 74645

RSI
COATING